

EUROBOND EBA641 Bearing Retainer

PRODUCT DESCRIPTION

EBA641 Bearing Retainer is a medium strength retaining compound designed for bonding cylindrical fitting parts where disassembly is required for servicing and repair operations. Ideal for parts that need subsequent dismantling, i.e., retention of bearings on shafts and in housings.

RETAINING COMPOUNDS

Techsil retaining Compounds have an anaerobic cure system, meaning it cures in the absence of air and the presence of metal ions. The resin remains liquid until it is confined between metal parts. Using Techsil Retainers when mounting cylindrical parts has distinct advantages over mechanical assemblies. Using retaining compounds allows a manufacturer to use slip-fitted parts with relaxed machining tolerances.

ANAEROBIC KEY FEATURES

- Increase assembly reliability
- Eliminate backlash in keys and splines
- Increase the strength of heavy press fits
- Eliminate fretting corrosion
- Seal against environmental corrosion
- Eliminate high assembly stresses
- Reduce variations in load transmission.

INSTRUCTIONS FOR USE

- Clean surfaces to be bonded with Techsil Surface cleaning wipes.
- Apply adhesive to the threads, apply sufficient adhesive to fill the voids and then assemble and tighten as required

LIMITATIONS

- This product is not recommended for use in pure oxygen and/or oxygen-rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials. Material removed from containers may be contaminated during use. Do not return product to the original container. Techsil Ltd will not assume responsibility for product that has been contaminated or stored under conditions other than those previously indicated.
- Anaerobic products are not normally recommended for use on plastics (particularly thermoplastic materials where stress cracking of the plastic could result). Users are recommended to confirm compatibility of the product with such substrates.

STORAGE

Store product in the unopened container in a dry area out of direct sunlight. Storage below 7°C or greater than 28°C can adversely affect product performance. If stored properly, this product has a shelf life of 12 months.

TECHNICAL FEATURES

Base technology	Dimethacrylate ester
Colour	Yellow
Cure	Anaerobic
Viscosity Brookfield Sp2@20rpm@25°C	400-800 cps
Gap fill	0.1mm
Cure speed without Activator	20-30 mins @ 22°C
Cure speed with Activator	<5 mins @ 22°C
Shelf Life	24 months @ 22°C
Specific Gravity ASTM D1475-13 (2020)	1.06
Temperature Range	-55°C to +150°C

TEST PERFORMANCE

Full Cure Time	12 hours @ 22°C
Static Strength – ISO4587	>6N/mm ²

TEST CRITERIA

The test performance data reported was measured according to ISO 4587 using M10 mild steel bolts and cured 24 hours at 22°C (71.6°F) before testing.

PACKAGING FORMAT

Bottles	10ml, 50ml, 250ml
---------	----------------------

HEALTH & SAFETY

This technical information sheet does not constitute a Safety Data Sheet (SDS). Before using this product ensure you have read and fully understood this products SDS.

Contact Details

TECHSiL Limited
Unit 34, Bidavon Industrial Estate, Waterloo Road, Bidford on Avon, Warwickshire, B50 4JN
+44(0)1789 773232 | sales@techsil.co.uk | www.eurobond-adhesives.co.uk

INSTRUCTIONS FOR USE

- Clean surfaces to be bonded with Techsil Surface cleaning wipes.
- Apply adhesive to the threads, apply sufficient adhesive to fill the voids and then assemble and tighten as required

LIMITATIONS

- This product is not recommended for use in pure oxygen and/or oxygen-rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials. Material removed from containers may be contaminated during use. Do not return product to the original container. Techsil Ltd will not assume responsibility for product that has been contaminated or stored under conditions other than those previously indicated.
- Anaerobic products are not normally recommended for use on plastics (particularly thermoplastic materials where stress cracking of the plastic could result). Users are recommended to confirm compatibility of the product with such substrates.

STORAGE

Store product in the unopened container in a dry area out of direct sunlight. Storage below 7°C or greater than 28°C can adversely affect product performance. If stored properly, this product has a shelf life of 12 months.

DISCLAIMER

This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any other process. Such information is, to the best of the company's knowledge and belief, accurate and reliable as of the date indicated. However, no warranty guarantee or representation is made to its accuracy, reliability or completeness. It is the user's responsibility to satisfy themselves as to the suitability of such information for their particular use.

Contact Details

TECHSiL Limited
Unit 34, Bidavon Industrial Estate, Waterloo Road, Bidford on Avon, Warwickshire, B50 4JN
+44(0)1789 773232 | sales@techsil.co.uk | www.eurobond-adhesives.co.uk