



TECHNICAL DATA SHEET – PLASTIC STEEL PUTTY (A)

Revised: 01/2017

ORDERING INFORMATION

STOCK NO.: 10112

PACKAGE SIZE: 500g

STOCK NO.: 10115

PACKAGE SIZE: 1kg

STOCK NO.: 10117

PACKAGE SIZE: 10Kg

DESCRIPTION

The original metal filled epoxy putty for economical, dependable maintenance and repair work.

RECOMMENDED APPLICATIONS

- Repairs cracks and breaks in equipment, machinery or castings
- Patches and rebuilds blow holes or pits in castings
- Rebuilds worn equipment, pumps and valve bodies
- Restores bearing journals and races

PRODUCT DATA

TYPICAL PHYSICAL PROPERTIES

COLOUR	Grey
MIX RATIO BY VOLUME	2.5:1
MIX RATIO BY WEIGHT	9:1
% SOLIDS BY VOLUME	100
POT LIFE AT 25°C/ MINS	45
SPECIFIC VOLUME CC/KG	429
CURED SHRINKAGE CM/CM	0.0006
SPECIFIC GRAVITY	2.33
TEMPERATURE RESISTANCE	Dry 121°C
COVERAGE	858cm ² /Kg @ 5mm
CURED HARDNESS / SHORE D	85 D
DIELECTRIC STRENGTH KV/MM	1.18
ADHESIVE TENSILE SHEAR / MPA	19
COMPRESSIVE STRENGTH MPA	57
COEFFICIENT OF THERMAL EXPANSION X10 ⁻⁶ CM/CM/°C	86.4
THICKNESS PER COAT / MM	As Required
FUNCTIONAL CURE TIME /HOURS	16
RECOAT TIME / MINUTES	4
MIXED VISCOSITY /CPS (WHERE APPLICABLE)	Putty

PLASTIC STEEL PUTTY (A)

THE ORIGINAL METAL FILLED EPOXY PUTTY

CHEMICAL RESISTANCE - 7 DAYS ROOM TEMPERATURE CURE (30 DAYS) - TESTING CARRIED OUT 30 DAYS IMMERSION AT 21°C

	POOR	FAIR	VERY GOOD	EXCELLENT
AMMONIA			•	
CUTTING OIL			•	
ISOPROPYL ALCOHOL	•			
GASOLINE (UNLEADED)			•	
HYDROCHLORIC ACID 37%			•	
METHYL ETHYL KETONE (MEK)	•			
METHYLENE CHLORIDE			•	
SODIUM HYPOCHLORITE 5% (BLEACH)			•	
SODIUM HYDROXIDE 50%			•	
SULPHURIC ACID 98%			•	
XYLENE		•		

Excellent = +/- 1% weight change, Very Good = +/- 1-10% weight change, Fair = +/- 10-20% weight change, Poor = > 20% weight change

APPLICATION INFORMATION

CURE

A 12.7mm thick section of Devcon Plastic Steel Putty will harden at 21°C in 4 hours. The material will be fully cured in 16 hours at which time the material can be machined, drilled or painted. The actual cure time of epoxy is determined by the mass used and the room temperature at time of repair.

SURFACE PREPARATION

Proper surface preparation is essential to a successful application. The following procedures should be considered:

- All surfaces must be dry, clean and rough.
- If the substrate surface is oily or greasy use MEK or similar solvent to degrease the surface.
- Remove all paint, rust and grime from the surface by abrasive blasting or other mechanical techniques.
- Aluminum repairs: Oxidation of aluminum surfaces will reduce the adhesion of an epoxy to a surface. This film must be removed before repairing the surface, by mechanical means such as grit-blasting or chemical means.
- Provide a "profile" on the metal surface by roughening the surface. This should be done ideally by grit blasting (8-40 mesh grit), or by grinding with a coarse wheel or abrasive disc pad. An abrasive disc may be used provided white metal is revealed. Do not 'feather edge' epoxy materials. Epoxy material must be 'locked in' by defined edges and a good 75 - 125 microns profile.
- Metal that has been handling sea water or other salt solutions should be grit blasted and high pressure water blasted and left overnight to allow any salts in the metal to 'sweat' to the surface. Repeat blasting may be required to 'sweat out' all the soluble salts. A test for chloride contamination should be performed prior to any epoxy application. A bristle test or similar can be used to evaluate the salt level. The maximum soluble salts left on the substrate should be no more than 40 p.p.m. (parts per million).
- Chemical cleaning with MEK or similar solvent should follow all abrasive preparation. This will help to remove all traces of sandblasting, grit, oil, grease, dust or other foreign substances.

- Under cold working conditions, optimum application can be achieved by heating the repair area to ~40° C immediately before applying any of Devcon's Metal-filled Epoxies is recommended. This procedure dries off any moisture, contamination or solvents and assists the epoxy in achieving maximum adhesion to the substrate.
- Always try to make the repair as soon as possible after cleaning the substrate, to avoid oxidation or flash rusting. If this is not practical, a general application of FL-10 Primer will keep metal surfaces from flash rusting.

MIXING

Plastic Steel Putty (A) is formulated to be a dense mix that can be applied easily to overhead and vertical surfaces without running or sagging. For the 500g and 1Kg kits, empty the Resin and hardener onto a mixing board and mix using a spatula. Do not mix in the containers. For the 10Kg kit, add the hardener to the resin and mix using a T shaped mixer or Jiffy ES mixer attached to a power drill. Fold the material by vigorously moving the mixer up and down until a uniform mix has been achieved. Once mixed, immediately spread out the mass of material onto a suitable area before use to avoid a rapid exotherm and associated reduction in potlife.

APPLICATION

For best results, product should be kept and applied at room temperature. Plastic Steel Putty (A) can be applied when temperatures are between 13°C and 52°C. Spread the putty over prepared surface with a putty knife. Press firmly to ensure maximum surface contact and avoid trapping air. To bridge large gaps or holes use fibreglass, sheet metal or wire mesh.

SHELF LIFE & STORAGE

A shelf life of 3 years from date of manufacture can be expected when stored at room temperature (22°C) in their original containers

PRECAUTION

For complete safety and handling information, please refer to Material Safety Data Sheets (MSDS) prior to using this product.

WARRANTY

ITW Engineered Polymers will replace any material found to be defective. As the storage, handling and application of this material is beyond our control we can accept no liability for the results obtained.

DISCLAIMER

All information on this data sheet is based on laboratory testing and is not intended for design purposes. ITW Engineered Polymers makes no representations or warranties of any kind concerning this data.

For product information visit www.devconeurope.com alternatively for technical assistance please call +353 61 771 500.