

Three Bond 1346B Thread Lock Low Strength

Product Outline

No matter what locking properties are required, one of ThreeBond's thread lock products will get the job done. All of ThreeBond's thread locks cure spontaneously when sealed off from contact with the air between close fitting metallic surfaces and inhibit the development of rust, leaks, corrosion and are not affected by oils, chemicals, salt water, various gases or solvents.

Features

- White label MSDS – no irritant marking.
- Low strength, frequent removal type.
- For bolts and small screws where disassembly with hand tools is required for servicing.
- Eliminates mechanical locking parts such as spring or toothed washers, nylon nuts etc.
- Reduces required fastening on torque.
- Completely seals against oil, water and most chemicals.
- Excellent vibration resistance.

Typical Properties

Properties	Value
Appearance	Blue liquid
Viscosity	2,500 mPa.s
Gap fill	0.3mm
Breakloose torque	14 Nm
Prevailing torque	7 Nm
Fixture time	≤ 10 minutes
Full cure time	≤ 24 hours
Temperature range	-60°C to + 150°C

Directions for Use

- After selecting the correct grade of ThreeBond thread lock, remove all dirt and oil. Parts must be clean.
- Apply ThreeBond thread lock to mating surfaces.
- Assemble immediately.
- Allow specified fixture time before disturbing the parts.
- Use primer TB3095C to improve cure speed and ensure curing in larger than specified gaps.

Handling precautions

- ThreeBond thread locks have been proven to be safe to handle as long as normal hygienic practices are observed.
- If there is a possibility of product splashing into the eyes it is recommended that eye protection is worn.
- Refer to the product MSDS for further details.
- Use and keep out of reach of children.

Storage

- Shelf life 12 months. Keep the container tightly sealed and store in a dry cool place avoiding direct sunlight.

Packaging

- 10g, 50g and 250g bottle.