



IS5628E

ONE COMPONENT FLOWABLE HIGH STRENGTH SILICONE ADHESIVE /SEALANT

Product Description

IS5628E one-component, ready-to-use, adhesive/sealant is a flowable consistency product specially developed for applications where high strength is required. On exposure to atmospheric moisture at room temperature this product cures to a very tough, durable, resilient silicone rubber. IS5628E utilizes an acetoxycure system, releasing small amounts of acetic acid vapours from the sealant during cure.

Key Performance Properties

- One-component, no mixing, easy-to-use
- Flowable
- Room temperature condensation cure
- Very high strength
- High and low temperature resistance (-60°C to +200°C)
- Excellent adhesion to silicone rubbers

Applications

- Bonding silicone HCR gaskets together
- Seam sealer
- Bonding silicone coated fabric.

Typical Product Data

| Typical uncured Properties | | |
|---------------------------------------------------|--------------------------------|------|
| Appearance | Translucent, flowable | |
| Viscosity at 23°C, | Pa·s | 175 |
| Tack-free Time at 23°C | Minutes | 10 |
| Selfleveling | mm | 75 |
| Typical cured Properties (3 days @ 20°C / 50% RH) | | |
| Appearance | translucent elastomeric rubber | |
| Density | g/cm ³ | 1.10 |
| Hardness | Shore A | 33 |
| Tensile strength | MPa | 7.5 |
| Elongation | % | 750 |
| Tear strength | kN/m | 15 |

Specifications

Typical product data values should not be used as specifications. Assistance and specifications are available by contacting Momentive performance materials Technical Service RTV1 and RTV2.



**Instructions
for Use**

Surface Preparation

IS5628E will bond to clean surfaces without the aid of primers. These surfaces typically include many metals, glass, ceramic, and silicone rubber. A preliminary check should be made to determine bonding effects for each specific application. For difficult-to-bond substrates, use of a primer will usually improve adhesion. Momentive performance materials silicone primers SS4004P, SS4044P and SS4179 are recommended for use with this adhesive/sealant.

Where adhesion is required, surfaces should be thoroughly cleaned with a suitable solvent such as iso propylalcohol (IPA) or methyl ethyl ketone (MEK) to remove dirt, oil and grease. The surface should be wiped dry before applying the adhesive/sealant.

Momentive performance materials Silicone IS5628E adhesive/sealant may be applied directly to clean substrate. Where broad surfaces are to be mated, sealant should be applied in a thin, less than 6 mm diameter, bead or ribbon around the edge of the surface to be bonded.

RTV adhesive/ sealants cure on exposure to moisture in the air at room temperature. The cure begins with the formation of a skin on the exposed surface of the sealant and progresses inward through the material. At 25°C and 50% relative humidity, this product will form a surface skin, which is tack free to the touch in 10 minutes. Once a skin has begun to form, further tooling of the adhesive is not advisable. High temperatures up to 70°C and high humidity will accelerate the cure process; low temperatures and low humidity will slow down the cure. During the initial stages of cure, a noticeable odour caused by the liberation of the acetic acid vapour is produced. This odour will totally disappear as the cure progresses

A 2 mm section of adhesive/sealant will cure through in 24 hours. Since cure time increases with thickness, use of IS5628E should be limited to section thicknesses of 6 mm.

For removing uncured adhesive/ sealants, solvent systems such as naphtha, methyl ethyl ketone (MEK) or trichloroethylene (TCE) are most effective.

After cure, selected chemical strippers, which will dissolve the silicone rubber, are available from other manufacturers. Specific product information may be obtained on request.

**Handling and
Safety**

Material Safety Data Sheets are available upon request from Momentive performance materials. Similar information for solvents and other chemicals used with the Momentive performance materials products should be obtained from your supplier. When solvents are used, proper safety precautions must be observed.

**Storage and
Warranty Period**

The shelf life will be indicated by the 'use before date' on the associated documents with a minimum of 4 months when stored in the original unopened containers below 27° C.

Availability

IS5628E is available in 310 ml cartridges, 20 kg pails and in 200 kg drums.



PRINCIPAL LOCATIONS – Regional Information

| | | | |
|------------------------------------------|-------------------------------------------------------------------------------|----------------------------------------|--------------------|
| North America | World Headquarters 187 Danbury Road Wilton, CT 06897, USA | T 800.295.2392 | F 607.754.7517 |
| Latin America | Rodovia Eng. Constâncio Cintra, Km 78,5 Itatiba, SP – 13255-700, Brazil | T +55.11.4534.9650 | F +55.11.4534.9660 |
| Europe, Middle East, Africa and India | D-51368 Leverkusen Germany | T 00.800.4321.1000 T +31.164.225350 | F +31.164.241.750 |
| Pacific | Akasaka Park Building - 5-2-20 Akasaka Minato-ku, Tokyo 107-6112 Japan | T +81.3.5544.3100 | F +81.3.5544.3101 |

CUSTOMER SERVICE CENTERS

| | | | |
|------------------------------------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------------|--------------------------------------------------------------------------------------|
| North America | Charleston, WV 25314, USA E cs-na.silicones@momentive.com | | |
| | <ul style="list-style-type: none"> Specialty Fluids UA, Silanes, Resins, and Specialties RTV Products-Elastomers Sealants and Adhesives & Construction | T 800.523.5862 T 800.334.4674 T 800.332.3390 T 877.943.7325 | F 304.746.1654 F 304.746.1623 F 304.746.1623 F 304.746.1654 |
| Latin America | E cs-la.silicones@momentive.com | | |
| | <ul style="list-style-type: none"> Argentina & Chile Brazil Mexico & Central America Venezuela, Ecuador, Peru, Colombia, & Caribbean | T +54.11.4862.9544 T +55.11.4534.9650 T +52.55.5899.5135 T +58.212.285.2149 | F +54.11.4862.9544 F +55.11.4534.9660 F +52.55.5899.5138 F +58.212.285.2149 |
| Europe, Middle East, Africa and India | E cs-eur.silicones@momentive.com | T 00.800.4321.1000 T +31.164.225350 | F +31.164.241750 |
| Pacific | E cs-ap.silicones@momentive.com | | |
| | <ul style="list-style-type: none"> Japan China Korea Singapore | T +81.276.20.6182 T +86.21.5050.4666 (ext. 1523) T +82.2.6201.4600 T +65.6220.7022 | |
| Worldwide Hotline | Worldwide Web www.momentive.com | T 800.295.2392 T +607.786.8131 | F +607.786.8309 |

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GmbH, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS. EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.